



VEIK
维凯

M602 >>>

PRODUCT CODE



杜邦™ Teflon® 商标
DuPont™ Teflon® Trademark

Teflon® 是杜邦公司商标
并授权江苏维凯科技股份有限公司使用

Items 项目	Unit 单位	M602	Method 测试方法
Thickness 厚度	mm	0.5±0.05	DIN EN ISO 2286-3
Weight 重量	g/m ²	900 ± 90	DIN EN ISO 2286-2
Tensile Strength 抗拉强度	Warp 径向	4500	DIN 53354
	Weft 纬向	4000	
Tear Resistance 撕裂强度	Warp 径向	350	DIN 53363
	Weft 纬向	350	
Overlapping Strength 接头强度 (搭接5~7cm)	Warp 径向	>4500	DIN 53354
	Weft 纬向	>4000	
Translucency 漂白后可视透光率		15	ASTM E 424
Solar Reflection 漂白后可视反光率	%	70±10	ASTM E 424
Basic Cloth 基布	%	Fiberglass 玻璃纤维	DIN 60001
Type of coating 涂层		PTFE	
Color 颜色		White (after exposure to sunlight) 日晒后变为白色	
Weaving 织法		Plain L 1/1	DIN ISO 9354

样本尺寸: 165mmX65mm

sample recommended for appropriate project
适合您工程项目的材料样品

* Values shown above are not standard values but average values.

本产品采用杜邦™ Teflon® 氟树脂生产, 不含PFOA

Teflon® logo is trademark or registered trademark of E.I. du Pont de Nemours and Company or its affiliates, and is used under license by Jiangsu VEIK Technology & Materials Co., Ltd.

销售中心: 上海维立凯膜材料有限公司
Shanghai Wei&Kai Membrane materials Co., Ltd.

T, +86 15190616800

生产基地: 江苏省泰兴市经济开发区开发路9号
Add, No. 9 Kaifa Road, Economic Development Zone, Jiangsu, China

网址: www.veik.cn